

GREASE COMPATIBILITY GUIDELINES



	Aluminum Complex	Barium	Calcium	Calcium 12-hydroxyesteric Acid	Calcium Complex	Clay	Lithium	Lithium 12-hydroxyesteric Acid	Lithium Complex	Polyurea	Sodium	Calcium Sulphonate	Silica
Aluminum Complex	○	×	×	✓	×	×	×	×	✓	×	×	×	✓
Barium	×	○	×	✓	×	×	×	×	×	×	×	M	✓
Calcium	×	×	○	✓	×	✓	✓	M	✓	×	×	N/A	N/A
Calcium 12-hydroxyesteric Acid	✓	✓	✓	○	M	✓	✓	✓	✓	×	×	N/A	N/A
Calcium Complex	×	×	×	M	○	×	×	×	✓	✓	×	✓	×
Clay	×	×	✓	✓	×	○	×	×	×	×	×	×	✓
Lithium	×	×	✓	✓	×	×	○	✓	✓	×	×	✓	✓
Lithium 12-hydroxyesteric Acid	×	×	M	✓	×	×	✓	○	✓	×	×	✓	N/A
Lithium Complex	✓	×	✓	✓	✓	×	✓	✓	○	×	×	✓	✓
Polyurea	×	×	×	×	✓	×	×	×	×	★	×	×	×
Sodium	×	×	×	×	×	×	×	×	×	×	○	×	×
Calcium Sulphonate	×	M	N/A	N/A	✓	×	✓	✓	✓	×	×	○	N/A
Silica	✓	✓	N/A	N/A	×	✓	✓	N/A	✓	×	×	N/A	○

○	Same Grease
✓	Compatible
×	Not Compatible
M	Moderately Compatible

★ NOTE: Not all polyurea greases are mutually compatible